

## Material Data Sheet

Trade name	PET MOD		
DIN EN ISO 1043 designation	PET		
Modification	PTFE		
Properties	Unit	Test method	Value
<b>General Properties</b>			
Density	g/cm <sup>3</sup>	DIN EN ISO 1183-1	1,44
Moisture absorption			
Saturation in air of 23°C/50% RH	%	DIN EN ISO 62	0,23
Saturation in water of 23°C	%	DIN EN ISO 62	0,47
Flammability acc.to UL 94 (Thickn. 3mm/6mm)		ISO 1210 (UL 94)	HB / HB
<b>Mechanical Properties</b>			
Yield point	MPa	DIN EN ISO 527	70
Elongation at break	%	DIN EN ISO 527	10
Tensile modulus of elasticity	MPa	DIN EN ISO 527	2.600
Notched impact strength (Charpy)	kJ/m <sup>2</sup>	ISO 179/1eA/Pendulum 1J	-
Ball indentation hardness	N/mm <sup>2</sup>	DIN EN ISO 2039-1	160
Shore - Hardness	Scale D	DIN 53505	-
<b>Thermal Properties</b>			
Melting temperature	°C	ISO 11357	255
Thermal conductivity	W/(mK)	DIN 52612	0,28
Specific thermal capacity	kJ/(kgK)	DIN 52612	-
Coefficient of linear thermal expansion	10 <sup>-6</sup> K <sup>-1</sup>	Average betw.20°C-60°C	65
Service temperature - long-term	°C		- 20 up to 115
Service temperature - short-term, max.	°C		180
Heat deflection temperature, Method A:1,8 MPa	°C	DIN EN ISO 75	75
<b>Electrical Properties</b>			
Dielectric constant, 50 Hz		IEC 60250	3,4
Dielectric dissipation factor, 50 Hz		IEC 60250	0,001
Volume resistivity	Ohm cm	IEC 60093	10 <sup>18</sup>
Surface resistivity	Ohm	IEC 60093	10 <sup>16</sup>
Comparative tracking index CTI, Sol. A		IEC 60112	600
Dielectric strength	kV/mm	IEC 60243	20

**Remarks:**

The short-term maximum application temperature only applies to very low mechanical stress for a few hours.  
The long-term maximum application temperature is based on the thermal ageing of plastics by oxidation, resulting in a decrease of the mechanical properties.  
This applies to an exposure to temperatures for at least 5.000 hours causing a 50% loss of the tensile strength from the original value (measured at room temperature). This value says nothing about the mechanical strength of the material at high application temperatures. In case of thick-walled parts, only the surface layer is affected by oxidation from high temperatures. With the addition of antioxidants, a better protection of the surface layer is achieved. In any case, the center area of the material remains unaffected.  
The minimum application temperature is basically influenced by possible stress factors like impact and/or shock under application. The values stated refer to an minimum degree of impact stress.  
The electrical properties as stated result from measurements on natural, dry material. With other colors (in particular black) or saturated material, there may be clear differences in the electrical properties.  
The values indicated result from numerous individual measurements for an approximation of the values and are to our today's knowledge. They serve as information about our products and are presented as a guide to choose from our range of materials. This, however, does not include an assurance of specific properties or the suitability for particular application purposes that are legally binding. Since the properties also depend on the dimension of the semi-finished products and the degree of crystallisation (e.g. nucleating by pigments), the actual values of the properties of a particular product may differ from the indicated values.  
\* The mechanical properties of fiber reinforced material were measured on injection molded samples, parallel to fiber direction.  
Special construction details of further material specifications on request.